

CHARACTERISTICS PORCELAIN (Group Bla)

DATE: 07/11/2017

MODEL: ACADIA BLANCO / GRIS SIZE 15X90	SERIE ACADIA CODE 200000000000013243		
1.-CLASIFICACION (UNE-EN 14411). Dry Pressed Ceramics Tiles with low water absorption - Group Bla, E ≤ 0.5% for internal and external floors and walls.			
2.-SPECIFICATIONS (UNE-EN 14.411 - ISO13.006)			
REQUIREMENTS	STANDARD APPLIED	REQUERIMENTS STANDARD	TEST RESULTS
Dimensions and Surface Quality	ISO 10545-2	---	PASS
Water Absorption	ISO 10545-3	E ≤ 0.5 %	PASS
Modulus of Rupture	ISO 10545-4	≥ 35 N/mm ²	PASS
MOHS	EN 101	(*)	6
Crazing Resistance	ISO 10545-11	(*)	PASS
Resistance to chemicals	ISO 10545-13	Min B	GA
- Household chemicals: Ammonium chloride solution 100 g/l		Min B	GA
- Swimming pool salts: Sodium Hypochlorite solution 20 mg/l		(*)	GLA
- Acids and alkalies:		(*)	GLA
Low concentrations: Hydrochloric acid solution (3%)		(*)	GLA
Citric acid solution 100 g/l		(*)	GLA
Potassium hydroxide 30 g/l		(*)	GHA
High concentrations: Hydrochloric acid solution (18%)	(*)	GHA	
Lactic acid solution (5%)	(*)	GHA	
Potassium hydroxide 100 g/l	(*)	GHA	
Resistance to staining:	ISO 10545-14	Min 3	5
Cr2O3/FE2O3 + light oil	ISO 10545-7	(*)	IV
Abrasion Resistance (PEI):	ISO 10545-12	Required	PASS
Frost Resistance	DIN 51130 (R)	(*)	R9
Slip resistance	ANSI 137.1 (DCOF)	(*)	>0.42
	JNE-ENV 12633(Clas)	(*)	27º/1

3.-APLICACION GROUPS
According to its characteristics, Hijos de F. Gaya Fores, defines this model as group:

GRUPO D

(*) as manufacturer confirms

1.- CLASIFICATION.

Water abs. production	Group I E ≤ 3 %	Group IIa 3 % < E ≤ 6 %	Group IIb 6 % < E ≤ 10 %	Group III E > 10 %
A Extruded	Group AI ISO 13006 Annex A1	Group AIIa ISO 13006 Annex A2a	Group AIIb ISO 13006 Annex A2b	Group AIII ISO 13006 Annex A3
B Dry pressed	Group BIa E ≤ 0.5 % ISO 13006 Annex B1a	Group BIb ISO 13006 Annex B2a	Group BIIb ISO 13006 Annex B2b	Group BIII ISO 13006 Annex B3
C Others	Group CI 0.5 < E ≤ 3 % ISO 13006 Annex B1b	Group CIIa	Group CIIb	Group CIII

2.-CHARACTERISTICS

RESISTANCE TO	CLASS	MEANING
Stains	5	The stain is removed with hot water and a damp cloth
	4	The stain is removed with a weak cleaning agent.
	3	The stain is removed with mechanical cleaning and a strong cleaning agent.
	2	The stain is removed with suitable solvent after immersion for 24 h.
	1	The stain is not removed
Household chemicals Swimming pool salts	GA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GB(V)	Definite change in appearance
	GCV(V)	Partial or complete loss of the original surface
Acids and alkalies Low concentrations (L)	GLA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GLB(V)	Definite change in appearance
	GLC(V)	Partial or complete loss of the original surface
High concentrations (H)	GHA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GBH(V)	Definite change in appearance
	GHC(V)	Partial or complete loss of the original surface

3.- APPLICATIONS GROUPS

- GROUP A.-** Recommended for moderate or low level transit. Suitable for bedrooms and/or bathrooms in houses (avoid any kind of abrasion).
- GROUP B.-** Suitable for light or medium transit, such as rooms inside houses, except for kitchens or areas with direct access from outside.
- GROUP C.-** Floorings recommended for medium transit, suitable for houses, all kind of rooms included kitchen or near to entrance area.
- GROUP D.-** Flooring suitable for heavy traffic, such as entrances to houses with direct access from the outside, all kind of rooms and professional offices.
- GROUP GRAN TRANSITO.-** Flooring suitable and recommended for very heavy traffic

CHARACTERISTICS PORCELAIN (Group Bla)

DATE: 07/11/2017

MODEL: ACADIA SPIGA BLANCO / GRIS SIZE 45X90	SERIE ACADIA CODE 200000000000013246		
1.-CLASIFICACION (UNE-EN 14411). Dry Pressed Ceramics Tiles with low water absorption - Group Bla, E ≤ 0.5% for internal and external floors and walls.			
2.-SPECIFICATIONS (UNE-EN 14.411 - ISO13.006)			
REQUIREMENTS	STANDARD APPLIED	REQUERIMENTS STANDARD	TEST RESULTS
Dimensions and Surface Quality	ISO 10545-2	---	PASS
Water Absorption	ISO 10545-3	E ≤ 0.5 %	PASS
Modulus of Rupture	ISO 10545-4	≥ 35 N/mm ²	PASS
MOHS	EN 101	(*)	6
Crazing Resistance	ISO 10545-11	(*)	PASS
Resistance to chemicals	ISO 10545-13	Min B	GA
- Household chemicals: Ammonium chloride solution 100 g/l		Min B	GA
- Swimming pool salts: Sodium Hypochlorite solution 20 mg/l		(*)	GLA
- Acids and alkalies:		(*)	GLA
Low concentrations: Hydrochloric acid solution (3%)		(*)	GLA
Citric acid solution 100 g/l		(*)	GLA
Potassium hydroxide 30 g/l		(*)	GHA
High concentrations: Hydrochloric acid solution (18%)	(*)	GHA	
Lactic acid solution (5%)	(*)	GHA	
Potassium hydroxide 100 g/l	(*)	GHA	
Resistance to staining:	ISO 10545-14	Min 3	5
Cr2O3/FE2O3 + light oil	ISO 10545-7	(*)	IV
Abrasion Resistance (PEI):	ISO 10545-12	Required	PASS
Frost Resistance	DIN 51130 (R)	(*)	R9
Slip resistance	ANSI 137.1 (DCOF)	(*)	>0.42
	JNE-ENV 12633(Clas)	(*)	27º/1

3.-APLICACION GROUPS
According to its characteristics, Hijos de F. Gaya Fores, defines this model as group:

GRUPO D

(*) as manufacturer confirms

1.- CLASIFICATION.

Water abs. production	Group I E ≤ 3 %	Group IIa 3 % < E ≤ 6 %	Group IIb 6 % < E ≤ 10 %	Group III E > 10 %
A Extruded	Group AI ISO 13006 Annex A1	Group AIIa ISO 13006 Annex A2a	Group AIIb ISO 13006 Annex A2b	Group AIII ISO 13006 Annex A3
B Dry pressed	Group BIa E ≤ 0.5 % ISO 13006 Annex B1a	Group BIb ISO 13006 Annex B2a	Group BIIb ISO 13006 Annex B2b	Group BIII ISO 13006 Annex B3
C Others	Group CI 0.5 < E ≤ 3 % ISO 13006 Annex B1b	Group CIIa	Group CIIb	Group CIII

2.-CHARACTERISTICS

RESISTANCE TO	CLASS	MEANING
Stains	5	The stain is removed with hot water and a damp cloth
	4	The stain is removed with a weak cleaning agent.
	3	The stain is removed with mechanical cleaning and a strong cleaning agent.
	2	The stain is removed with suitable solvent after immersion for 24 h.
	1	The stain is not removed
Household chemicals Swimming pool salts	GA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GB(V)	Definite change in appearance
	GCV(V)	Partial or complete loss of the original surface
Acids and alkalies Low concentrations (L)	GLA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GLB(V)	Definite change in appearance
	GLC(V)	Partial or complete loss of the original surface
High concentrations (H)	GHA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GBH(V)	Definite change in appearance
	GHC(V)	Partial or complete loss of the original surface

3.- APPLICATIONS GROUPS

- GROUP A.-** Recommended for moderate or low level transit. Suitable for bedrooms and/or bathrooms in houses (avoid any kind of abrasion).
- GROUP B.-** Suitable for light or medium transit, such as rooms inside houses, except for kitchens or areas with direct access from outside.
- GROUP C.-** Floorings recommended for medium transit, suitable for houses, all kind of rooms included kitchen or near to entrance area.
- GROUP D.-** Flooring suitable for heavy traffic, such as entrances to houses with direct access from the outside, all kind of rooms and professional offices.
- GROUP GRAN TRANSITO.-** Flooring suitable and recommended for very heavy traffic



Designs for your lifestyle

Exclusive Distributors:
 MIR Group, Inc.
 2200 B Zanker Rd, San Jose, CA 95131
 Ph: +1 408 432-5400,
 +1 408 432-1000
 fax: +1 408 228-3924
 e-mail: info@mir-mosaic.com
 www.facebook.com/mir.mosaic
 www.mir-mosaic.com

ACADIA

ACADIA




ACADIA BLANCO
Size: 5.9x35.4"



ACADIA SPIGA BLANCO
Size: 17.7x35.4"



ACADIA GRIS
Size: 5.9x35.4"



ACADIA SPIGA GRIS
Size: 17.7x35.4"